



# TECHNICAL DATA SHEET

## TriRoof HPX Hybrid Polymer Liquid Membrane Repair Kit



Revision date: 23/08/24  
Revision number: (0)

### Product Description

TriRoof HPX Hybrid Polymer Liquid Membrane is a premium, cold applied, one-component based polymer. This elastic, waterproofing membrane is free of bitumen, solvent and isocyanates. Once fully cured, it forms a waterproof, UV resistant surface that repairs cracks up to 5mm. The HPX repair kit is designed for temporary repairs before a full HPX application is applied to the entire roof substrate.

### Applications

Protection, repair, restoration and waterproofing of the following surface and areas:

- Concrete floor slabs and roofs
- Small horizontal movement joints
- As a flexible coating of roofs
- Waterproofing of wet areas (under-tile) in bathrooms, kitchens, balconies, auxiliary rooms, etc.

### Product Features

- Can be applied to damp surfaces
- Good resistance to UV, water and moisture
- Self-leveling
- Solvent-free, non-flammable
- Apply by brush, roller or spatula
- Breathable until cured, allowing moisture to evaporate
- Environmentally friendly – Free of bitumen, isocyanate and solvents

### Storage & Shelf life

- Protected from water, frost and adverse air conditions
- Keep dry and cool on wooden pallets at between +10°C and +25°C in moisture free conditions
- The opened products should be consumed immediately
- Shelf life is maximum 9 months conditional to complying with the aforementioned storage conditions

## Typical Specifications

TECHNICAL DATA	
Base	Hybrid Polymer
Density (g/ml)	1,44 (ASTM D1875)
Colour	Light Grey
Curing Rate	3,05 m/day
Viscosity	10000-20000 cps Brookfield DV-E RV 23°C Spindle No 05
Hardness (Shore A)	30±5 ISO 868
% Elongation	Min. 300% (DIN 53504)
Tensile Strength (N/mm <sup>2</sup> )	1-1,5 (DIN 53504)
Application Temperature	+5 °C to +35 °C
Product Temperature	+5 °C to +25 °C
Temperature Resistance (Cured Product)	-20 °C to +80 °C

## APPLICATION PROCEDURE

### Surface Preparation

- All loose materials must be removed by brushing, scraping or high-pressure water.
- Surfaces should be clean and free from any oil, grease, debris, or other contaminants that may affect adhesion.
- All surfaces should be degreased, either with acetone or detergent and washed off thoroughly.
- Any organic growth should be treated with a fungicidal wash.
- New concrete and mortars must be at least 28 days old.
- Metal surfaces should be clean and free from rust and or flaking debris.

### Application

1. Ensure the substrate is free from contaminants and no standing water is present.
2. Accurate measurement and cutting of the Chopped Strand Matting (CSM) is crucial. Ensure the Matting is cut to the correct size for the repair area, and be mindful to keep it dry during this process.
3. Cut open the foil pack at one end only.
4. Squeeze the foil pack so HPX covers the area you need to repair – do not use all of the pack, as you will need more of the product to cover the Matting.
5. Using the Brush in the kit, spread the HPX around the repair area, ensuring a thin spread of HPX is evenly applied to the substrate.
6. Use the Brush to place the Matting into the HPX and ensure it is adequately tacked down.
7. After the Matting is adequately tacked into the first layer, applying the remaining HPX is essential. This step ensures a strong bond and a smooth finish.
8. Allow for a small border (15mm) of HPX liquid to be between the outer edge of the CSM Matting and where the HPX liquid is to meet the substrate again.
9. Allow the application to cure for a minimum of 2-3 hours before rain.
10. Inspect the finished surface. If pinholes are present, scuff the affected area with 80-grit Sandpaper, wipe with Acetone and apply a thin layer of HPX with a spreader over the affected area.

### Coverage

- Indicatively: 0.5 - 0.7 sqm per kit

## Precautions

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Material Safety Data Sheet containing physical, ecological, toxicological and other safety-related data.

## Legal Notice

The technical data contained herein is based on our present knowledge and experience and we cannot be held liable for any errors, inaccuracies, omissions or editorial failings that result from technological changes or research between the date of issue of this document and the date the product is acquired. Before using the product, the user should carry out any necessary tests in order to ensure that the product is suitable for the intended application. Moreover, all users should contact the seller or the manufacturer of the product for additional technical information concerning its use if they think that the information in their possession needs to be clarified in any way, whether for normal use or a specific application of our product. Our guarantee applies within the context of the statutory regulations and provisions in force, current professional standards and in accordance with the stipulations set out in our general sales conditions. The information detailed in the present technical data sheet is given by way of indication and is not exhaustive. The same applies to any information provided verbally by telephone to any prospective or existing customer.

## Get in touch.



Tricel Composites (GB) Ltd.

Unit A, Fox Way, Off Atkinson St., Leeds, LS10 1PS.

Tricel Composites (NI) Ltd.

Unit 4, Milltown Industrial Estate, Warrenpoint,  
Co.Down, BT34 3FN.



+ 44 (0) 113 270 3133



sales@triroof.co.uk

[www.triroof.co.uk](http://www.triroof.co.uk)